



MICRONAIRE (MIC)




	0	0	11	122	2.724	2.899	0	5.756
Fardos	0	0	11	122	2.724	2.899	0	5.756
Média Ponderada	0,00	0,00	3,75	3,91	4,19	4,43	0,00	4,30
Porcentagem	0,00%	0,00%	0,19%	2,12%	47,32%	50,36%	0,00%	100,00%

COMPRIMENTO (LEN)




	0	4	362	2.128	3.133	128	1	5.756
Fardos	0	4	362	2.128	3.133	128	1	5.756
Média Ponderada	0,00	26,85	27,71	29,06	30,15	31,36	32,79	29,62
Porcentagem	0,00%	0,07%	6,29%	36,97%	54,43%	2,22%	0,02%	100,00%

RESISTÊNCIA (STR)




Fardos	0	0	110	965	2.027	2.220	434	5.756
Média Ponderada	0,0	0,0	27,7	28,9	30,4	31,8	32,9	30,8
Porcentagem	0,00%	0,00%	1,91%	16,77%	35,22%	38,57%	7,54%	100,00%

UNIFORMIDADE (UNF)




Fardos	0	0	73	2.609	3.005	69	0	5.756
Média Ponderada	0,0	0,0	79,5	81,6	83,3	85,2	0,0	82,5
Porcentagem	0,00%	0,00%	1,27%	45,33%	52,21%	1,20%	0,00%	100,00%

ALONGAMENTO (ELG)




Fardos	0	0	687	3.529	1.381	153	6	5.756
Média Ponderada	0,0	0,0	6,1	6,5	6,9	7,5	8,1	6,6
Porcentagem	0,00%	0,00%	11,94%	61,31%	23,99%	2,66%	0,10%	100,00%

ÍNDICE DE FIBRAS CURTAS (SFI)



Fardos	6	808	2.608	1.870	409	55	0	5.756
Média Ponderada	5,5	7,1	8,0	9,0	10,5	11,7	0,0	8,4
Porcentagem	0,10%	14,04%	45,31%	32,49%	7,11%	0,96%	0,00%	100,00%

GRAU DE REFLECTÂNCIA (RD)




Fardos	0	1	174	2.917	2.664	0	0	5.756
Média Ponderada	0,0	64,9	69,0	73,3	76,1	0,0	0,0	74,5
Porcentagem	0,00%	0,02%	3,02%	50,68%	46,28%	0,00%	0,00%	100,00%

GRAU DE AMARELAMENTO (+B)




Fardos	0	0	2	239	4.166	1.265	84	5.756
Média Ponderada	0,0	0,0	6,9	7,8	8,5	9,3	10,2	8,7
Porcentagem	0,00%	0,00%	0,03%	4,15%	72,38%	21,98%	1,46%	100,00%

GRAU DE FOLHA (LEAF)



Fardos	44	222	945	1.545	1.525	939	536	5.756
Média Ponderada	1	2	3	4	5	6	7	5
Porcentagem	0,76%	3,86%	16,42%	26,84%	26,49%	16,31%	9,31%	100,00%


MATURIDADE (MAT)



Fardos	0	0	0	0	24	4.391	1.341	5.756
Média Ponderada	0,00	0,00	0,00	0,00	0,84	0,86	0,87	0,86

Porcentagem	0,00%	0,00%	0,00%	0,00%	0,42%	76,29%	23,30%	100,00%
-------------	-------	-------	-------	-------	-------	--------	--------	----------------

ÍNDICE DE FIABILIDADE (SCI)



Fardos	1	26	304	1.250	2.322	1.683	170	5.756
Média Ponderada	99	107	116	125	135	143	152	135
Porcentagem	0,02%	0,45%	5,28%	21,72%	40,34%	29,24%	2,95%	100,00%