



MICRONAIRE (MIC)




Fardos	4.059	7.604	22.995	15.039	10.936	5.680	3	66.316
Média Ponderada	3,16	3,40	3,65	3,89	4,12	4,48	5,01	3,80
Porcentagem	6,12%	11,47%	34,67%	22,68%	16,49%	8,57%	0,00%	100,00%

COMPRIMENTO (LEN)




Fardos	0	2.265	17.471	33.780	12.167	632	1	66.316
Média Ponderada	0,00	26,57	27,59	28,82	30,10	31,38	32,74	28,68
Porcentagem	0,00%	3,42%	26,35%	50,94%	18,35%	0,95%	0,00%	100,00%

RESISTÊNCIA (STR)




	ABAIXO DE 26,00	DE 26,00 A 26,99	DE 27,00 A 27,99	DE 28,00 A 29,49	DE 29,50 A 30,99	DE 31,00 A 32,99	ACIMA 33,00	TOTAL GERAL
Fardos	1.364	3.752	16.377	23.572	15.879	5.059	313	66.316
Média Ponderada	25,4	26,5	27,5	28,8	30,2	31,6	32,7	28,9
Porcentagem	2,06%	5,66%	24,70%	35,54%	23,94%	7,63%	0,47%	100,00%

UNIFORMIDADE (UNF)




	ABAIXO DE 75,00	DE 75,00 A 77,49	DE 77,50 A 79,99	DE 80,00 A 82,59	DE 82,60 A 84,59	DE 84,60 A 86,49	ACIMA 86,50	TOTAL GERAL
Fardos	0	57	18.883	38.741	8.552	83	0	66.316
Média Ponderada	0,0	77,2	79,1	81,1	83,1	85,3	0,0	80,8
Porcentagem	0,00%	0,09%	28,47%	58,42%	12,90%	0,13%	0,00%	100,00%

ALONGAMENTO (ELG)




Fardos	0	4	6.343	45.454	12.781	1.603	131	66.316
Média Ponderada	0,0	5,4	6,1	6,5	6,9	7,5	8,1	6,6
Porcentagem	0,00%	0,01%	9,56%	68,54%	19,27%	2,42%	0,20%	100,00%

ÍNDICE DE FIBRAS CURTAS (SFI)




Fardos	281	2.462	7.703	24.996	21.962	8.683	229	66.316
Média Ponderada	5,6	6,9	8,0	9,2	10,6	11,9	13,3	9,8
Porcentagem	0,42%	3,71%	11,62%	37,69%	33,12%	13,09%	0,35%	100,00%

GRAU DE REFLECTÂNCIA (RD)




	ABAIXO DE 60,00	DE 60,00 A 64,99	DE 65,00 A 69,99	DE 70,00 A 74,99	DE 75,00 A 79,99	DE 80,00 A 84,99	ACIMA 85,00	TOTAL GERAL
Fardos	1	5	454	15.333	24.925	25.598	0	66.316
Média Ponderada	58,5	63,1	68,6	73,4	77,8	81,5	0,0	78,1
Porcentagem	0,00%	0,01%	0,68%	23,12%	37,59%	38,60%	0,00%	100,00%

GRAU DE AMARELAMENTO (+B)




	ABAIXO DE 5,00	DE 5,00 A 5,99	DE 6,00 A 6,99	DE 7,00 A 7,99	DE 8,00 A 8,99	DE 9,00 A 9,99	ACIMA 10,00	TOTAL GERAL
Fardos	0	6	3.233	28.672	21.271	12.605	529	66.316
Média Ponderada	0,0	5,7	6,7	7,5	8,4	9,3	10,4	8,1
Porcentagem	0,00%	0,01%	4,88%	43,24%	32,08%	19,01%	0,80%	100,00%

GRAU DE FOLHA (LEAF)



Fardos	15.014	14.785	18.038	11.146	4.632	1.843	858	66.316
Média Ponderada	1	2	3	4	5	6	7	3
Porcentagem	22,64%	22,29%	27,20%	16,81%	6,98%	2,78%	1,29%	100,00%


MATURIDADE (MAT)



Fardos	0	0	56	6.211	26.873	31.272	1.904	66.316
Média Ponderada	0,00	0,00	0,79	0,82	0,84	0,85	0,87	0,84

Porcentagem	0,00%	0,00%	0,08%	9,37%	40,52%	47,16%	2,87%	100,00%
-------------	-------	-------	-------	-------	--------	--------	-------	----------------

ÍNDICE DE FIABILIDADE (SCI)



Fardos	103	3.841	15.219	22.165	17.195	6.712	1.081	66.316
Média Ponderada	97	106	115	125	134	143	153	126
Porcentagem	0,16%	5,79%	22,95%	33,42%	25,93%	10,12%	1,63%	100,00%